

Pedrali SpA

SP 122 - 24050 Mornico al Serio - Bergamo - Italia

Ufficio Commerciale Italia +39 035 8358810

Export Dept. +39 035 8358840


Fax +39 035 8358888

www.pedrali.it - info@pedrali.it

RIPIANO / TOP / TISCHPLATTE / PLATEAU / SOBRE

BAW/50

design Pedrali R&D



MATERIALE STRATO SUPERFICIALE Material / Material / Matériau couche superficielle / Material	Laminato, finitura gofrata Laminate, textured finish / Laminatplatte, texturisiert / Stratifié, finition gaufrée / Laminado, acabado gofrado
ANIMA Core / Kern / Coeur / Alma	MDF
BORDO Edge / Kante / Chant / Canto	Piatto, in ABS wengé Flat, wenge ABS / Flache, ABS wengé / Plat, ABS wengé / Recto, ABS wengue
SPESSORE Thickness / Stärke / Épaisseur / Espesor	50 mm
MISURE Sizes / Abmessungen / Dimensions / Medidas	* Tolleranza dimensionale ± 5 mm / Dimensional tolerance ± 5 mm Tondo / Round / Runder / Rond / Redondo: Ø490 mm - Ø590 mm - Ø690 mm - Ø790 mm - Ø890 mm - Ø990 mm - Ø1190 mm - Ø1290 mm Quadrato / Square / Viereckig / Carré / Cuadrado: 590x590 mm - 690x690 mm - 790x790 mm - 890x890 mm Rettangolare / Rectangular / Rechteckig / Rectangulaire / Rectangular: 1190x790 mm - 1390x790 mm - 1590x790 mm
UTILIZZO Usage / Verwendung / Usage / Uso	Indoor
NORMATIVE Regulations / Bestimmungen / Réglementations / Normativas	Resistenza all'abrasione EN 438-2.10 (Giri IP ≥ 150 e A ≥ 350) / Resistance to surface wear EN 438-2.10 (Revs IP ≥ 150 e A ≥ 350) Resistenza al graffio EN 438-2.25 (grado ≥ 3) / Resistance to scratching EN 438-2.25 (rating ≥ 3) Resistenza alle macchie EN 438-2.26 (grado 5) / Resistance to staining EN 438-2.26 (rating 5) Solidità del colore alla luce EN 438-2.27 (grado ≥ 4) / Lightfastness EN 438-2.27 (rating ≥ 4) Resistenza alle bruciature di sigaretta EN 438-2.30 (grado ≥ 3) / Resistance to cigarette burns EN 438-2.30 (rating ≥ 3) Emissione di formaldeide EN 13986 (E1) / Formaldehyde emission EN 13986 (E1) Adesione delle finiture al supporto UNI 9240:1987 (3,2) Rapporto di prova CATAS 106449 / Test Catas report 106449 / Testbericht Catas 106449 / Rapport d'essai Catas 106449 / Prueba n° 106449